

Re-Roll Unsupported NTPEP

Unsupported NTPEP is a woven geotextile made up of polypropylene filaments. These filaments are woven to form a stable and durable network such that the filaments retain their relative position. It is non-biodegradable and resistant to most soil chemicals, acids, and alkali with a pH range of 3 to 12. Unsupported NTPEP is manufactured to meet or exceed the following minimum average roll values:

PROPERTY	TEST METHOD	ENGLISH	METRIC
Fabric			
Grab Tensile	ASTM D4632	125 x 125 lbs	0.550 x 0.550 kN
Elongation	ASTM D4632	15 x 15 %	15 x 15 %
UV Resistance	ASTM D4355	80 % @ 500 hrs	80 % @ 500 hrs
AOS ¹	ASTM D4751	30 US Std. Sleeve	0.60 mm
Permittivity	ASTM D4491	0.10 sec⁻¹	0.10 sec⁻¹
Flow Rate	ASTM D4491	8 gpm/ft²	325.6 Lpm/m²

¹ Maximum Average Roll Value

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.