

TerraCell® 280

Material

TerraCell® 280 is a perforated, textured geocell manufactured from High Density Polyethylene (HDPE) to the following minimum standards:

Fabrication

TerraCell® 280 sections are manufactured from 58 strips of HDPE; each of appropriate height by 142 inches (3.6m) long. Typical panels are 29 cells long and 5 cells wide. Cell walls are textured with a multitude of rhomboidal indentations with a surface density of 22 to 31 per cm² (140 to 200 per in²). Perforations remove 16% ± 3% of the cell wall. Cell joints are ultrasonically spot-welded with 3 welds per inch uniformly spaced across the height of each strip. Seam strengths are the same across the entire height of the cell joint and meet the minimum tensile requirements below:

Seam Hang Strength

Seam Hang Strength – A 102 mm (4.0 in.) weld joint supporting a load of 72.5 kg (160 lbs.) for 30 days minimum or a 102 mm (4.0 in.) weld joint supporting a load of 72.5 kg (160 lbs.) for 7 days minimum while undergoing temperature change from 23° C (74° F) to 54° C (130° F) on a 1 hour cycle.

Dimensions

TerraCell® 280, in expanded configuration, has nominal dimensions of 3, 4, 6 and 8 inch cell depths with an optimal width of 8.4 feet and optimal length of 45 feet. Optimal panel expanded area is 378 ft² (35.14m²). Other panel lengths can be custom-made; panel length is simply a function of number of strips welded. Unexpanded spacing of weld joints is 28 inches. Optimal cell area is 20 inches by 18.7 inches nominal. Individual cell area is 187 square inches (1206 cm²) nominal.

Additional Information

The quality control system used in the manufacturing of TerraCell® is in compliance with ISO9001:2000 standards. TerraCell® is licensed from the United States Army under Patent No. 4,797,026. Please contact Hanes Geo Components, or a TerraCell® distributor for more information.

PROPERTY	TEST METHOD	ENGLISH	METRIC
Material			
Nominal Sheet Thickness Before Texturing ¹	ASTM D5199	50, +10%, -5% mils	1.270, +10%, -5% mm
Nominal Sheet Thickness After Texturing ¹	ASTM D5199	60, +10%, -5% mils	1.524, +10%, -5% mm
Density	ASTM D1505	0.540 - 0.558 oz/in ³	0.935 - 0.965 g/cm ³
Carbon Black Content	ASTM D1603	1.5 %	1.5 %
Environmental Stress Crack Resistance	ASTM D1693	6000 hours	6000 hours
Environmental Stress Crack Resistance	ASTM D5397	>400 hours	>400 hours
Fabrication			

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.

PROPERTY	TEST METHOD	ENGLISH	METRIC
Seam Peel Strength ²		-	-
8" Cell Depth (Nominal Panel Weight - 114 lbs)		640 lbs	2847 N
6" Cell Depth (Nominal Panel Weight - 86 lbs)		480 lbs	2135 N
4" Cell Depth (Nominal Panel Weight - 57 lbs)		320 lbs	1423 N
3" Cell Depth (Nominal Panel Weight - 43 lbs)		240 lbs	1068 N

1 Mean of 10 measurements

2 Seam Peel Strength per U. S. Army Corps of Engineers Technical Report GS-86-19, Appendix A

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.