

TerraTex® N06E

TerraTex® N06E is a nonwoven geotextile made up of polypropylene fibers. These fibers are needed to form a stable and durable network such that the fibers retain their relative position. It is non-biodegradable and resistant to most soil chemicals, acids, and alkali with a pH range of 3 to 12. TerraTex® N06E is manufactured to meet or exceed the following minimum average roll values:

Unless noted otherwise, all values are minimum average roll values (MARV).

PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight ¹	ASTM D5261	6.0 oz/yd ²	203 g/m ²
Thickness	ASTM D5199	85 mils	2.16 mm
Grab Tensile	ASTM D4632	160 lbs	0.711 kN
Grab Elongation	ASTM D4632	50 %	50 %
Trapezoid Tear	ASTM D4533	65 lbs	0.290 kN
CBR Puncture	ASTM D6241	450 lbs	2.00 kN
Permittivity ¹	ASTM D4491	1.63 sec ⁻¹	1.63 sec ⁻¹
Permeability ¹	ASTM D4491	0.30 cm/sec	0.30 cm/sec
Water Flow Rate ¹	ASTM D4491	125 gpm/ft ²	5,080 Lpm/m ²
AOS ^{1, 2}	ASTM D4751	70 US Std. Sieve	0.212 mm
UV Resistance	ASTM D4355	70 % @ 500 hrs	70 % @ 500 hrs

¹ At the time of manufacturing. Handling, storage, and shipping may change these properties.

² Value represents maximum average roll value.

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.