

Flexamat Plus UV-T Specification

1. DESCRIPTION

A Tied Concrete Block Mat with Triple Layered Underlayment and manufactured with a UV stabilized interlocking geogrid. This work shall consist of furnishing and placing the system in accordance with this specification and conforming with the lines, grades, design, and dimensions shown on the plans.

2. MATERIALS

Flexamat Plus UV-T is manufactured from individual concrete blocks tied together with high strength UV resistant polypropylene bi-axial geogrid. Each block is tapered, beveled and interlocked and includes connections that prevent lateral displacement of the blocks within the mats when they are lifted for placement.

Tied Concrete Block Mat with Triple Underlayment UV-T shall be Flexamat Plus UV-T, manufactured by Motz Enterprises, Inc.

- 2.1. **Blocks.** Furnish blocks manufactured with concrete conforming to the cement requirements of ASTM C150 and to the aggregate requirements of ASTM C33. Meet a minimum compressive strength of 6,900 psi at 28 days. Furnish blocks that have a minimum weight of 3 lbs. per block and placed no further than 2 in. apart. Material shall have a weight per square foot not exceeding 10 lbs. Blocks shall have a 2.25" profile, a flat-top pyramid shape, and a coarse finish without protrusions. Concrete shall have a minimum compressive strength requirement of Table1, certified by a third party.

Table 1
Concrete Compressive Strength Requirements

Age	Required Compressive Strength psi
7 - Day	5000 psi
14 - Day	6000 psi
28 - Day	6900 psi

- 2.2. **Polypropylene Bi-Axial Geogrid.** The interlocking geogrid shall be composed of polypropylene multifilament yarns knitted in tension and designed to resist degradation in environments with exposure to ultra-violet light, water and low pH (<4 pH) and high pH (>9 pH). Carbon black UV inhibitor shall be blended into to the extruded yarns at a rate no less than 0.8% by weight and the knitted geogrid shall be coated with an initial coating to independently achieve a maximum Tensile Strength loss of 8% at 500 hours when tested in accordance with ASTM D4355. The geogrid shall then be subsequently coated with a high ultra-violet resistant synthetic rubber blend coating with a tan color (for identification). When combined with the revetment mat, this will yield a durable, high tenacity, low elongating, and continuous filament polypropylene fibers that is securely cast into and embedded within the base of the concrete blocks and obtains connection strength greater than that of the geogrid. Ensure the geogrid meets physical and ultra-violet resistance requirements of Table 2.

Table 2 - Polypropylene Bi-Axial Geogrid Requirements

Property	Unit	Test	Requirement
Mass/Unit Area	oz/yd ²	ASTM D5261	6.5 oz/yd ²
Aperture Size	English units	Measured	1.4 x 1.4 inch
Ultimate Wide Width Tensile Strength (MD x CMD)	lb/ft	ASTM D6637	2,055 lb/ft
Elongation at Ultimate Tensile Strength (MD x CMD)	%	ASTM D6637	≤ 8%
Wide Width Tensile Strength @ 2% (MD x CMD)	lb/ft	ASTM D6637	822 lb/ft
Wide Width Tensile Strength @ 5% (MD x CMD)	lb/ft	ASTM D6637	1,640 lb/ft
Tensile Modulus @ 2% (MD x CMD)	lb/ft	ASTM D6637	41,100 lb/ft
Tensile Modulus @ 5% (MD x CMD)	lb/ft	ASTM D6637	32,800 lb/ft
UV Resistance (4000 hr)	% retained/hr	ASTM G154	100% Retained Strength
Color	Color Chart	Visual	Tan

2.3. **Triple Underlayment material included within rolls** – System underlayment material are required to be packaged within the tied concrete block mat rolls to ensure proper installation.

Flexamat Plus UV-T – A four-layered system must include, in order from top to bottom, 1) Concrete block mat 2) 5-Pick Leno Weave 3) Recyclax TRM-V and 4) Curlex® II. The underlayment materials shall be packaged within the roll of the Flexamat Plus UV-T.


5000 PSI Concrete Blocks

UV-T High Strength Biaxial Geogrid

5-Pick Leno Weave

Recyclax® TRM

Curlex® II Wood Excelsior



Leno Weave Five-Pick Weave:

This is a woven, white polypropylene netting that provide added strength and support to the underlayments.

<u>Index Property</u>	<u>Units</u>	<u>Value</u>
GSM	g/m ²	118 (-3 ~ +3)
Density	Picks/10cm	62 x 24 (+/- 2)
Warp Strength	N/5cm	≥ 350
Warp Elongation	%	20 - 50
Weft Strength	N/5cm	≥ 280
Weft Elongation	%	20 - 50
Warp Shrinkage	%	≤ 7

²SLR is the Soil Loss Ratio, as reported by NTPEP/AASHTO. ³ Bench-scale index values should not be used for design purposes.

- 2.4. Cover the Flexamat Plus UV-T or otherwise protect it during long periods of storage to protect against degradation of the backing material as recommended by the manufacturer.
- 2.5. Mats will be rolled for shipment and packaged with lifting straps. Upon delivery, rolls may be left exposed for up to 30 days. If exposure will exceed 30 days, cover or tarp the rolls to minimize exposure.

All mats to be inspected upon delivery. Assure that all units are sound and free of defects that would interfere with the proper placing of the unit or impair the strength or permanence of the construction.

Chipping or missing concrete resulting in a weight loss exceeding 15% of the average weight of a concrete unit is grounds for rejection by the engineer. Replace, repair or patch the damaged areas per the manufacturer's recommendations.

3. PERFORMANCE

Full-Scale laboratory testing performed by an independent 3rd party testing facility with associated engineered calculations certifying the hydraulic capacity of the proposed TCBM meets the following requirements:

Test	Tested Value	Bed Slope	Soil Classification	Limiting Value
ASTM 6460	Shear Stress	30%	Sandy Loam (USDA)	24lb./ft ²
ASTM 6460	Velocity	20%	Loam (USDA)	30 ft./sec

4. ALTERNATIVE PRODUCTS

Such products must be pre-approved in writing by the Engineer prior to bid date. Alternative product packages must be submitted to the Engineer a minimum of fifteen (45) days prior to bid date. Submittal packages for alternate products must include, as a minimum, the following:

- 4.1. Alternative Product Properties – Product must be comprised of materials as detailed in Section 2, including both in composition, underlayment layers and performance requirements.
- 4.2. Full-Scale laboratory testing performed by an independent 3rd party testing facility with associated engineered calculations certifying the hydraulic capacity of the proposed Tied-Concrete Block Erosion Control Mat meets the performance requirements listed in Section 3 of this specification.
- 4.3. A list of 15 comparable projects in terms of material used, project size, and application in the United States, where the results of the specific alternative material's use can be verified and reviewed for system integrity and sustained after a minimum of 10 years of service life.

5. EQUIPMENT

Provide the proper equipment to place the mat that will not damage the mat material or disturb the soil subgrade and seed bed.

6. CONSTRUCTION

Prior to installing Flexamat Plus UV-T, prepare the subgrade as detailed in the plans. All subgrade surfaces to be smooth and free of all rocks, stones, sticks, roots, and other protrusions or debris of any kind that would result in an individual block being raised more than 3/4 in. above the adjoining blocks. When seeding is shown on the plans, provide subgrade material that can sustain growth.

Ensure the prepared subgrade provides a smooth, firm, and unyielding foundation for the mats. The subgrade shall be graded into a parabolic or trapezoidal shape to concentrate flow to middle of mat or mats.

Distribute seed on the prepared topsoil subgrade before installation of the tied concrete block mats in accordance with the specifications.

Install mats to the line and grade shown on the plans and per the specification. The manufacturer or authorized representative will provide technical assistance during preparation and installation of the concrete block mats as needed.

Provide a minimum 18 in. deep concrete mat embedment toe trench at all edges exposed to concentrated flows. Recess exterior edges subject to sheet flow a minimum of 6 in.

Areas that require mat seams parallel to concentrated flows are required to install mats with an interlocking geogrid and underlayment extension on the long edge for overlapping and anchoring the adjacent mat. Extensions shall be comprised of the mat's interlocking geogrid and all three layers of the Plus underlayment system.

Provide fastening or anchoring as recommended by the manufacturer or engineer for the site conditions.

7. MEASUREMENT

This Item will be measured by the square footage used, complete in place.

8. PAYMENT

The work performed, and materials furnished in accordance with this Item and measured as provided under "Measurement" will be paid for at the unit price bid for Flexamat Plus UV-T. This price is full compensation for loading and transporting, placing concrete block mats; excavation and disposal; furnishing topsoil and bedding; and equipment, labor, materials, tools, and incidentals.