

TerraDrain® Sheet 203

TerraDrain® Sheet 203 prefabricated drains are constructed using a high strength, high flow capacity, formed polystyrene core with a woven filter fabric bonded to one side. The filter fabric is bonded to each dimple to prevent soil intrusion into the core flow channels while allowing water to freely enter the drain core. The core provides an uninterrupted path for water to flow to designated drainage exits.

TerraDrain® Sheet 203 products are designed for subsurface, single-sided drainage applications requiring high compressive strength and flow capacity. TerraDrain® Sheet 203 is constructed using AASHTO M 288-06 Class 2 filter fabric.

PROPERTY	TEST METHOD	ENGLISH	METRIC
Fabric			
Material ¹		PP	PP
Water Flow Rate	ASTM D4491	160 gpm/ft²	6520 Lpm/m²
Grab Tensile Strength	ASTM D4632	410 x 220 lbs	1.824 x 0.979 kN
CBR Puncture Resistance	ASTM D6241	725 lbs	3.22 kN
Apparent Opening Size	ASTM D4571	45 US Std. Sieve	0.354 mm
Permittivity	ASTM D4491	2.3 sec⁻¹	2.3 sec⁻¹
Grab Elongation	ASTM D4632	15 %	15 %
UV Resistance	ASTM D4355	90 % @ 500 hrs	90 % @ 500 hrs
AASHTO M 288-06 ²	Survivability	Class 2 & 3	Class 2 & 3
Core			
Material ¹		HIPS	HIPS
Thickness	ASTM D1777	0.44 in	11 mm
Compressive Strength	ASTM D1621	18000 lbs/ft²	862 kPa
Installed Horizontal Flow Rate ³	ASTM D4716	4.1 gpm/ft	51 Lpm/m
Flow Rate ³	ASTM D4716	21 gpm/ft	261 Lpm/m

¹ PP = Polypropylene; HIPS = High Impact Polystyrene

² AASHTO Designation: M 288-06 Standard Specification for Highway Applications; American Association of State Highway and Transportation Officials, 2006. Geotextile survivability classification from installation stresses in subsurface drainage applications.

³ In-plane flow rate measured at 3,600 psf (172 kPa) compressive load and a hydraulic gradient of 1.0.

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.